



S.A.P.I.C.I. Spa  
 20063 Cernusco sul Naviglio (MI)  
 Via Bergamo, 2  
 Tel. (02) 921871  
 Fax (02) 92141949  
 www.sapici.it

## DATA SHEET

Issue date : 07/10/11  
 Last review date :  
 Edition N°: 1  
 Page : 1 of 1

### POLURENE LP 1810

<b>Type of Polymer:</b>	TDI based polyurethane prepolymer containing blocked isocyanic groups.	
<b>Range of use:</b>	In combination with cycloaliphatic diamines to formulate highly flexible , one-component stoving coatings	
<b>Specifications:</b> (°) DATA SHOWN ON CERTIFICATE OF ANALYSIS	<b>POLURENE LP 1810</b>	
	Appearance	Clear
	% NV	100
	% Free NCO	0,2 MAX (°)
	% Blocked NCO	2,7 ~ 3,2
	Viscosity (23°C mPa*s)	35000 ± 10000 (°)
	Colour (Gardner 1953)	1 MAX
<b>Application condition:</b>	POLURENE LP 1810 is combined with aliphatic diamines to formulate stoving coatings , solvent free high-building coatings and primer surfacers for automotive industry	
<b>Storage and warranty:</b>	In sealed drums we guarantee a shelf life of six months, provided POLURENE LP 1810 is stored under dry and cool condition. Storage at high temperatures can lead to an increase of viscosity of the product.	

The technical information provided in this sheet or given in oral or written form is based on our best knowledge and experience. These data, even technical and safety ones, are only suggestions, so they don't have to be considered as binding. The customer must test our products, technical assistance and information, to define to its satisfaction whether they are suitable for the intended use and application. The use, manufacture and the application conditions of our products are carried out beyond our control so they are under customer's responsibility. Sapici SpA guarantees the constant quality of the product, sales and delivery conditions.