

# 安鋒實業股份有限公司

台灣省台中市工業區 24 路 29 號 TEL:886-4-23501155 (代表) FAX:886-4-23507373  
E-mail:anvictor@ms45.hinet.net 網站: www.twanfong.com

---

## Solid acrylic resin AC-0591

### Product properties:

Type	: IBMA copolymer
Appearance	: white, clear, free flowing spherical beads
Solid content (%w/w)	: min 99 %
Tg (°C)	: 5
Average Mol. weight (Mw)	: 60000
Acid value	: <1
Viscosity (25°C; mPa.s)	: 500-700 (40% in Mixture) Mixture : Butyl acetate(2) / MIBK(1)
Density	: 1.05

### Solubility and compatibility:

AC-0591 is soluble in ketones, aromatics and esters. Hydroxyl groups available for cross-linking.

### Applications:

1. Coating for flexible substrates.
2. 2K isocyanides system for flexible substrates.

### End-use properties:

1. Soft and flexible.
2. Broad compatibility.
3. Good adhesion.

### Storage:

Stored in a dry place, its shelf life is 2 years.

### Remark :

This data is base on our current knowledge, it is correct and complete. However, it shall not constitute a guarantee for any specific product features. The customer is responsible to proof the data to be suitable for their own purposes.