

安鋒實業股份有限公司

台灣省台中市工業區 24 路 29 號 TEL:886-4-23501155 (代表) FAX:886-4-23507373
E-mail:anvictor@ms45.hinet.net 網站: www.twanfong.com

Solid acrylic resin AC-0514

Product properties:

Type	: Styrene copolymer
Appearance	: white, clear, free flowing spherical beads
Solid content (%w/w)	: min 99 %
Tg (°C)	: 72
Average Mol. weight (Mw)	: 108000
Acid value	: 27
Viscosity (25°C; mPa.s)	: 2500-3500 (40% in Toluene)
Softening point	: 135
Density	: 1.16

Solubility and compatibility:

AC-0514 is soluble in ketones, aromatics and esters.

Good compatible with NC, plasticizers and some acrylics.

Applications:

1. Plastic coatings.
2. Road paints.
3. Concrete paints.

End-use properties:

1. Hard and durable.
2. Chemical resistant.
3. High solids soluble.
4. Good properties on asphalt and concrete.

Storage:

Stored in a dry place, its shelf life is 2 years

Remark :

This data is based on our current knowledge, it is correct and complete. However, it shall not constitute a guarantee for any specific product features. The customer is responsible to proof the data to be suitable for their own purposes.