

安鋒實業股份有限公司

台灣省台中市南屯區工業區 24 路 29 號 TEL:886-4-23501155 (代表) FAX:886-4-23507373

E-mail:anvictor@ms45.hinet.net

網站 : www.twanfong.com

Solid acrylic resin AC-0517

Product properties :

| | |
|--------------------------|--|
| Type | : Styrene copolymer |
| Appearance | : white, clear, free flowing spherical beads |
| Solid content (%w/w) | : min 99 % |
| Tg (°C) | : 56 |
| Average Mol. weight (Mw) | : 85000 |
| Acid value | : 5 |
| Viscosity (25°C; mPa.S) | : 450~650 (40% in Toluene) |
| Softening point | : 135 |
| Density | : 1.05 |

Solubility and compatibility :

AC-0517 is soluble in ketones, white spirit, aromatics and esters. Good compatible with thickeners, plasticizers and other acrylics.

Applications :

1. Marine and metal paints.
2. Concrete paints.
3. Wall paints.
4. Road paints.

End-use properties :

1. Good hardness.
2. Chemical resistant.
3. High gloss.
4. Good outdoor durability.

Storage :

Stored in a dry place, its shelf life is 2 years.

Remark :

This data is base on our current knowledge, it is correct and complete. However, it shall not constitute a guarantee for any specific product features. The customer is responsible to proof the data to be suitable for their own purposes.