

安鋒實業股份有限公司

台灣省台中市工業區 24 路 29 號 TEL:886-4-23501155 (代表) FAX:886-4-23507373

E-mail:anvictor@ms45.hinet.net

網站:www.twanfong.com

KETONE-FORMALDEHYDE RESIN L2

Product:

L2 dissolves readily in alcohol(except methanol), in ketones, in esters and in low chlorinated hydrocarbons.

Specification :

Viscosity at 20°C (50% solution in butyl acetate/butanol)	: 35~60 mPas
Softening point	: 95~105°C
Water content	: < 4%
Acid value	: < 0.3 mg KOH/g
Iodine colour scale of 50% solution in butyl acetate/butanol	: < 2

Properties :

L2 is a high efficient binder in the manufacture of varnishes, varnish paints for the surface treatment of wood, metal and paper. First of all it is characterized by its good solubility, fast drying, neutrality and unsaponifiability.

L2 gives varnishes and painting materials and outstanding drying capacity from the drying of surface to hardening through, higher fastness to light and hardeness.

L2 resin is readily compatible with aminoplastics, a wide range of alkyd resins(drying and non-drying), epoxyesters, chlorinated rubber phenolic resins and polyester resins. With modified resins, ester and alcohol soluble cellulose nitrate as well as with any grades of plasticizers L2 is also readily compatible.

Packing :

25 kg per bag.

Store :

This product must be stored at 5~35°C where is shady and cool drying place and keep away sunshine and fire.

The above information is correct and complete, but it is without warranty. It is users' responsibilities to make sure that the product is suitable to satisfy their requests.

大陸手機:1350-9624401(技術),1382-5211745(業務)

第1頁,共2頁(第一版 2008.01)

安鋒實業股份有限公司

台灣省台中市工業區 24 路 29 號 TEL:886-4-23501155 (代表) FAX:886-4-23507373

E-mail:anvictor@ms45.hinet.net

網站:www.twanfong.com
