

# 安鋒實業股份有限公司

台灣省台中市工業區 24 路 29 號 TEL:886-4-23501155 (代表) FAX:886-4-23507373

E-mail:anvictor@ms45.hinet.net

網站：www.twanfong.com

---

## Chartwell AP-D525.3

### GENERAL DESCRIPTION:

A carboxy functional organic adhesion promoter synthesized using a **STABILIZED BIMETAL PRECURSOR**. The product is supplied in dipropylene glycol to aid in rapid dispersion and solubilization in most high solids coatings.

### PHYSICAL PROPERTIES:

Physical form	Clear liquid
Color	pale yellow
Metal content (Total %)	5.2-5.9
Complexed organics	9.1-9.3
Specific gravity (g/ml)	1.14
pH (2% soln)	3.50
Active matter (wt %)	25.3
Solvent	dipropylene glycol
Organofunctionality	carboxy

### APPLICATION:

(1) **Coatings:** Recommended for enhancing adhesion of high solid polyester melamine, acrylic melamine, and alkyd melamine crosslinked coatings to all metals. Also observed are improved salt fog resistance and reduced coating surface defects due to poor metal preparation and washing.

(2) **Pigment dispersion:** Recommended for pigment dispersion of difficult to disperse pigments, ei phthalo blue/ green, carbon black, etc. Also for all inorganic pigments, conductive pigments, and mineral fillers.

### PROCEDURE: HIGH SHEAR MIXING NECESSARY IN ALL SOLVENT-BORNE SYSTEMS

1. Add to grind stage at 1.0-2.0 phr. Disperse in resin and solvent before addition of melamine if possible.

\*Must be high shear mixed with a Cowles type mixer. Milling alone is not sufficient