

GRANDAL 3400

Aluminium Pellets



Schlenk Metallpulver GmbH & Co.KG
Barnsdorfer Hauptstr. 5
D-91154 Roth-Barnsdorf
Tel. +49(9171)808-0
Fax. +49(9171)808-200
www.schlenk.de

Application Service
Barnsdorfer Hauptstr. 12 – 14
D-91154 Roth-Barnsdorf
Tel. +49(9171)808-331
Fax.+49(9171)808-204

Technical Datas:

Metal content:

Mean particle diameter¹⁾:

Resin:

1) laser granulometry (Sympatec Helos)

Typical Analysis:

approx. 95 %

approx. 34 µm

urea-aldehyde resin

Characteristics:

- Coarse non-leafing aluminium pellets

Application:

- Colouring plastic materials
- Masterbatches



Recommendation for processing:

Recommended rate of pigmentation: 0,05 – 3 %

Heavy mechanical loads can result in finer aluminium particles and a greying of the aluminium colour shade.

Date of issue: 03.06.2005

Data contained in this publication are based on careful investigations and are intended for information only. Any user is obliged to carry out tests under his own responsibility as to the suitability of the product for a particular use and to investigate the possible violation of industrial property rights of third parties. Information is therefore not binding and cannot be construed as guaranteeing specific properties of products as established by law. Any liability as to the exactness and completeness of data is thus excluded. We apply our General Sales Conditions.

