POWDAL 170 VP/11428

Aluminium Powder



Schlenk Metallpulver GmbH & Co.KG Barnsdorfer Hauptstr. 5 D-91154 Roth-Barnsdorf Tel. +49 (0) 9171 808-0 Fax. +49 (0) 9171 808-200 www.schlenk.de Application Service Barnsdorfer Hauptstr. 12 – 14 D-91154 Roth-Barnsdorf Tel. +49 (0) 9171 808-332 Fax.+49 (0) 9171 808-204


Motor covered 1).	min 40000 cm²/m
Water coverage¹):	min. 40000 cm²/g
Residue on sieve 45 µm²):	max. 0,5 %
Mean particle diameter ³⁾ :	approx. 6 µm

Characteristics:

- Extremely fine leafing aluminium powder with good whiteness
- · Pigment shape: flake

Application:

Powder coatings





Recommendation for processing:

Recommended rate of pigmentation: 0,2 - 2 %

We advise the application with corona- and tribo-loading as well

