

# POWDAL 3250 XT

Aluminium Powder



Schlenk Metallpulver GmbH & Co.KG  
Barnsdorfer Hauptstr. 5  
D-91154 Roth-Barnsdorf  
Tel. +49 (0) 9171 808-0  
Fax. +49 (0) 9171 808-200  
www.schlenk.de

Application Service  
Barnsdorfer Hauptstr. 12 – 14  
D-91154 Roth-Barnsdorf  
Tel. +49 (0) 9171 808-332  
Fax.+49 (0) 9171 808-204

## Technical Data:

### Surface treatment:

**Residue on sieve 75 µm:**

**Mean particle diameter<sup>1)</sup>:**

## Typical Analysis:

### silica encapsulation

**max. 1 %**

**approx. 48 µm**

1) laser granulometry (Sympatec Helos)

## Characteristics:

- Very coarse non-leafing aluminium powder
- Pigment shape: silver dollar
- Excellent chemical resistance and weatherability

## Application:

- Powder coatings

Used in full-tone aluminium and tinted effect finishes as well



## Recommendation for processing:

Recommended rate of pigmentation: 0,5 - 4 %

We advise the application with corona-loading

Date of issue: 10.11.2006

Data contained in this publication are based on careful investigations and are intended for information only. Any user is obliged to carry out tests under his own responsibility as to the suitability of the product for a particular use and to investigate the possible violation of industrial property rights of third parties. Information is therefore not binding and cannot be construed as guaranteeing specific properties of products as established by law. Any liability as to the exactness and completeness of data is thus excluded. We apply our General Sales Conditions.

