

AWA 40096

Aluminium Paste



Schlenk Metallpulver GmbH & Co.KG
Barnsdorfer Hauptstr. 5
D-91154 Roth-Barnsdorf
Tel. +49 (0)9171 808-0
Fax. +49 (0)9171 808-200
www.schlenk.de

Application Service
Barnsdorfer Hauptstr. 12 – 14
D-91154 Roth-Barnsdorf
Tel. +49 (0)9171 808-331
Fax.+49 (0)9171 808-204

Technical Data:

Typical Analysis:

Non volatile content:

60 ± 2%

Solvent:

Water

Residue on sieve 45µm¹⁾:

max. 0,1%

Mean particle diameter²⁾:

approx. 15 µm

Surface treatment

phosphororganic


1) acc. to DIN 53196, 2) laser granulometry (Sympatec Helos)

Characteristics:

- Non leafing aluminium pigment for waterborne systems
- Pigment structure: Silverdollar

Application:

- Automotive and accessories coatings
- Industrial coatings
- Coil coatings
- Chrome effect/decoration and reflective coatings
- Aerosols, DIY



Recommendation for processing:

Recommended rate of pigmentation:

Full tone: 5 - 10 %

Metal effect: 2 - 6 %

The stability of the paste is guaranteed for at least 6 months, stored at room temperature and in closed rooms.

It is recommended to check the stability of the paste with each new batch no matter if already tested or material from a new delivery is taken.

The ingredients of the varnish such as resins, additives and even water may differ from batch to batch and affect the relevant stability characteristics of the aluminium pigment negatively.

Be aware of our technical information about aluminium pigments for waterborne systems, please. (TI019)

Date of issue: 22.02.2006

Data contained in this publication are based on careful investigations and are intended for information only. Any user is obliged to carry out tests under his own responsibility as to the suitability of the product for a particular use and to investigate the possible violation of industrial property rights of third parties. Information is therefore not binding and cannot be construed as guaranteeing specific properties of products as established by law. Any liability as to the exactness and completeness of data is thus excluded. We apply our General Sales Conditions.

