

## 各種粘度標準換算表

標準粘度 (厘泊)	格式管		KU 值	回轉粘度計 (100Kg荷重)	思格勒 粘度計 (100Kg荷重)	福特杯 4#	DIN粘度杯 (秒)			尼爾克杯 (秒)	塗-4# 粘度(秒)	塗-1# 粘度(秒)
	號數	氣泡秒數					2#	3#	4#			
10	A-4			3.5	94	11	16			2	10	2.5
25	A-2			9.5	190	16	19			3	14	3.5
50	A		30	19.5	350	20	23			4	18	4.5
65	B					26	27			5	22	6.0
85	C					34	33			6	28	7.0
100	D	1.46	40	40.7	750	40	38	12	10	7	30	7.5
125	E	1.83				46	46			8	32	8.0
140	F	2.05	46	53.0	1050	51	51	16	13	9	38	9.5
165	G	2.42				57	60			10	42	10.1
180	GH	2.64	50	70	1350	60		23	16	11	45	11.0
200	H	2.93	52	77	1500	65		26	17	12	50	12.0
225	I	3.30				75		28	20	14	57	14.0
250	J	3.67	57		1870	85		30	21	16	65	16.0
275	K	4.03				96		32	22	18	73	18.0
300	L	4.40	60	114	2250	108		34	24	20	80	20.0
320	M	4.70		118		117		35	25	22	88	22.0
340	N	5.00		125		123		37	27	31	123	31.0
370	O	5.40		138		127		39	28	32.0	128	32.0
400	P	5.80	64	150	3000	131		42	30	33.0	133	33.0
435	Q	6.40				137		45	32	35.0	138	34.0
470	R	6.90				144		48	34	36.5	144	
480	R*	7.13	67	183	3600	147				37.0	147	
500	S	7.30	68	191	3725	154		50	36		154	
550	T	8.10	69	204		166		54	39		166	
627	U	9.20						60	43			
800	U.V.	11.60	77	293	6000							
884	V	13.00							50			
1000	W	15.70		354	7500							
1400	X	18.90	96	498	10350							
1500	X*	21.10	98	539	11100							
2300	Y.Z	25.80	105	827	16800							
2500	Z <sub>1</sub>	39.60	114	893	18250							
3400	Z <sub>2</sub>	49.85	125									
4500	Z <sub>3</sub>	67.90	136	1610	32400							
6500	Z <sub>4</sub>	91.00		2310	46000							
10000	Z <sub>5</sub>	144.50		3580	674							
15000	Z <sub>6</sub>	217.10			105000							